

Amendment and Response
U.S. Serial No. 09/884,172
Page 3

COPY OF CLAIMS SUBMITTED W/AMDT ON
MARKED-UP COPY OF CLAIMS AS AMENDED

12/02/02

1. (Amended) A method of fabricating a CMOS inverter comprising:
providing a heterostructure including a Si substrate, a relaxed $\text{Si}_{1-x}\text{Ge}_x$ layer on
said Si substrate, and a strained surface layer on said relaxed $\text{Si}_{1-x}\text{Ge}_x$ layer, the
heterostructure comprising a planarized surface located between the strained surface layer
and the Si substrate and having a surface roughness less than 1 nm; and
integrating a pMOSFET and an nMOSFET in said heterostructure, wherein the
channel of said pMOSFET and the channel of said nMOSFET are formed in said strained
surface layer.

~~2. The method of claim 1, wherein the heterostructure further comprises a
planarized surface positioned between the strained surface layer and the Si substrate.~~

~~3. The method of claim 1, wherein the surface roughness of the strained surface
layer is less than 1 nm.~~

13. (Amended) A method of fabricating an integrated circuit comprising:
providing a heterostructure having a Si substrate, a relaxed $\text{Si}_{1-x}\text{Ge}_x$ layer on said
Si substrate, and a strained layer on said relaxed $\text{Si}_{1-x}\text{Ge}_x$ layer; ~~and~~
planarizing a surface between the strained layer and the Si substrate to a surface
roughness less than 1 nm; and

Amendment and Response
U.S. Serial No. 09/884,172
Page 4

forming a p transistor and an n transistor in said heterostructure, wherein said strained layer comprises the channel of said n transistor and said p transistor, and said n transistor and said p transistor are interconnected in a CMOS circuit.

~~14. The method of claim 13, wherein the heterostructure further comprises a planarized surface positioned between the strained layer and the Si substrate.~~

~~15. The method of claim 13, wherein the surface roughness of the strained layer is less than 1nm.~~

Amendment and Response
U.S. Serial No. 09/884,172
Page 5

CLEAN COPY OF ALL PENDING CLAIMS

1. (Amended) A method of fabricating a CMOS inverter comprising:
providing a heterostructure including a Si substrate, a relaxed $\text{Si}_{1-x}\text{Ge}_x$ layer on said Si substrate, and a strained surface layer on said relaxed $\text{Si}_{1-x}\text{Ge}_x$ layer, the heterostructure comprising a planarized surface located between the strained surface layer and the Si substrate and having a surface roughness less than 1 nm; and
integrating a pMOSFET and an nMOSFET in said heterostructure, wherein the channel of said pMOSFET and the channel of said nMOSFET are formed in said strained surface layer.
4. The method of claim 1, wherein the heterostructure further comprises an oxide layer positioned between the relaxed $\text{Si}_{1-x}\text{Ge}_x$ layer and the Si substrate.
5. The method of claim 1, wherein the heterostructure further comprises a SiGe graded buffer layer positioned between the relaxed $\text{Si}_{1-x}\text{Ge}_x$ layer and the Si substrate.
6. The method of claim 1, wherein the strained surface layer comprises Si.
7. The method of claim 1, wherein $0.1 < x < 0.5$.

Amendment and Response
U.S. Serial No. 09/884,172
Page 6

8. The method of claim 7, wherein the ratio of gate width of the pMOSFET to the gate width of the nMOSFET is approximately equal to the ratio of the electron mobility and the hole mobility in bulk silicon.

9. The method of claim 7, wherein the ratio of gate width of the pMOSFET to the gate width of the nMOSFET is approximately equal to the ratio of the electron mobility and the hole mobility in the strained surface layer.

10. The method of claim 7, wherein the ratio of gate width of the pMOSFET to the gate width of the nMOSFET is approximately equal to the square root of the ratio of the electron mobility and the hole mobility in bulk silicon.

11. The method of claim 7, wherein the ratio of gate width of the pMOSFET to the gate width of the nMOSFET is approximately equal to the square root of the ratio of the electron mobility and the hole mobility in the strained surface layer.

12. The method of claim 7, wherein the gate drive is reduced to lower power consumption.

13. (Amended) A method of fabricating an integrated circuit comprising:
providing a heterostructure having a Si substrate, a relaxed $\text{Si}_{1-x}\text{Ge}_x$ layer on said Si substrate, and a strained layer on said relaxed $\text{Si}_{1-x}\text{Ge}_x$ layer;

Amendment and Response
U.S. Serial No. 09/884,172
Page 7

planarizing a surface between the strained layer and the Si substrate to a surface roughness less than 1 nm; and

forming a p transistor and an n transistor in said heterostructure, wherein said strained layer comprises the channel of said n transistor and said p transistor, and said n transistor and said p transistor are interconnected in a CMOS circuit.

16. The method of claim 13, wherein the heterostructure further comprises an oxide layer positioned between the relaxed $\text{Si}_{1-x}\text{Ge}_x$ layer and the Si substrate.

17. The method of claim 13, wherein the heterostructure further comprises a SiGe graded buffer layer positioned between the relaxed $\text{Si}_{1-x}\text{Ge}_x$ layer and the Si substrate.

18. The method of claim 13, wherein the strained layer comprises Si.

19. The method of claim 13, wherein $0.1 < x < 0.5$.

20. The method of claim 13, wherein the CMOS circuit comprises a logic gate.

21. The method of claim 13, wherein the CMOS circuit comprises a NOR gate.

Amendment and Response
U.S. Serial No. 09/884,172
Page 8

22. The method of claim 13, wherein the CMOS circuit comprises an XOR gate.
23. The method of claim 13, wherein the CMOS circuit comprises a NAND gate.
24. The method of claim 13, wherein the p-channel transistor serves as a pull-up transistor in said CMOS circuit and the n-channel transistor serves as a pull-down transistor in said CMOS circuit.
25. The method of claim 13, wherein the CMOS circuit comprises an inverter.
26. A method of fabricating a CMOS inverter comprising:
providing a graded $\text{Si}_{1-x}\text{Ge}_x$ layer on a first Si substrate;
providing a relaxed $\text{Si}_{1-y}\text{Ge}_y$ layer on said graded layer to form a first structure;
bonding said relaxed layer of said first structure to a second structure that includes a second Si substrate;
removing said first Si substrate and said graded layer;
providing a strained surface layer on said relaxed layer to form a heterostructure;
and
integrating a pMOSFET and an nMOSFET in said heterostructure, wherein the channel of said pMOSFET and the channel of said nMOSFET are formed in said strained surface layer.
27. A method of fabricating an integrated circuit comprising:

Amendment and Response
U.S. Serial No. 09/884,172
Page 9

providing a graded $\text{Si}_{1-x}\text{Ge}_x$ layer on a first Si substrate;

providing a relaxed $\text{Si}_{1-y}\text{Ge}_y$ layer on said graded layer to form a first structure;

bonding said relaxed layer of said first structure to a second structure that includes a second Si substrate;

removing said first Si substrate and said graded layer;

providing a strained surface layer on said relaxed layer to form a heterostructure;

and

forming a p transistor and an n transistor in said heterostructure, wherein said strained layer comprises the channel of said n transistor and said p transistor, and said n transistor and said p transistor are interconnected in a CMOS circuit.